

TEST REPORT



1325 North 108th E. Ave.  
Tulsa, OK 74116  
918.437.8333 ph. | 918.437.8487 fx.

**CLIENT:**


Thea Inc.  
DbA Roxipan US  
4564 Via Maria  
Santa Barbara, CA 93111  
USA

Attn.: Myriam Doussineau


<b>Test Report No: TJ1326-2</b>	<b>Date: June 10, 2013</b>
---------------------------------	----------------------------

- SAMPLE ID:** The test samples are identified as ROXIFLOOR 1 specimens of flooring.
- SAMPLING DETAIL:** Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.
- DATE OF RECEIPT:** Samples were received in good condition at QAI on May 23, 2013
- TESTING PERIOD:** May 28, 2013
- AUTHORIZATION:** Testing authorized by Myriam Doussineau via QAI Proposal SP051413-3.
- TEST PROCEDURE:** ASTM F1914-07, Standard Test Method for Short-Term Indentation and Residual Indentation of Resilient Floor Covering.
- TEST RESULTS:** Detailed test results are presented in the subsequent pages of this report.

**PREPARED BY**

  
**Rocky Hale**  
Materials Testing Technician

**SIGNED FOR AND ON BEHALF OF  
QAI LABORATORIES, INC.**

  
**Randall Baker**  
Plumbing and Materials Managerger



---

## Test Results

---

Sample ID: ROXIFLOOR 1  
Room Conditions During Testing: 70°F / 50% Relative Humidity  
Load Used During Testing: 75 lb  
Flat Indenter Foot: 0.25" Dia.  
Indentation (Load) Time: 15 minutes  
Recovery Time: 1 hour

### Results:

Sample No.	Initial Thickness, in.	Final Thickness, in.	Difference, in.
1	0.485	0.482	0.003
2	0.496	0.493	0.003
3	0.489	0.486	0.003
Average	-	-	<b>0.003 or 0.6%</b>

\*\*\*\*\*

**End of Report**